## What is claimed is;

1. A copolymer of ethylene and  $\alpha$ -olefin of from 4 to 20 carbon atoms having melt flow rate of from 1 to 100, melt tension at 190°C (MT), intrinsic viscosity ([ $\eta$ ]) and a chain length A satisfying following formula (1) to (3), wherein the chain length A is a chain length at peak position of a logarithm normal distribution curve of a component having the highest molecular weight among logarithm normal distribution curves obtained by dividing a chain length distribution curve obtained by gel permeation chromatography measurement into at least two logarithm normal distribution curves,

$$2 \times MFR^{-0.59} < MT < 20 \times MFR^{-0.59}$$
 formula (1)  
 $1.02 \times MFR^{-0.094} < [\eta] < 1.50 \times MFR^{-0.156}$  formula (2)  
 $3.30 < logA < -0.0815 \times log(MFR) + 4.05$  formula (3).

2. A copolymer of ethylene and  $\alpha$ -olefin of from 4 to 20 carbon atoms having melt flow rate (MFR) of from 1 to 100, melt tension at 190°C (MT), intrinsic viscosity ([ $\eta$ ]) and characteristic relaxation time at 190°C ( $\tau$ ; unit is sec) satisfying the following formulas:

$$2 \times MFR^{-0.59} < MT < 20 \times MFR^{-0.59}$$
 formula (1)  
 $1.02 \times MFR^{-0.094} < [\eta] < 1.50 \times MFR^{-0.156}$  formula (2), and  
 $2 < \tau < 8.1 \times MFR^{-0.746}$  formula (4).

3. The copolymer of ethylene and  $\alpha$  -olefin according

to Claim 1 or 2, wherein the copolymer of ethylene and  $\alpha$  -olefin has activation energy for melt flow of not less than 60 kJ/mol.

4. The copolymer of ethylene and  $\alpha$ -olefin according to Claim 1 or 2, wherein the copolymer of ethylene and  $\alpha$ -olefin has swell ration (SR) and [ $\eta$ ] satisfying following formula (6).

when  $[\eta] < 1.20$ ,  $-0.91x[\eta] + 2.232 < SR < 2$ when  $[\eta] \ge 1.20$ , 1.17 < SR < 2.